

	Type	L #	Hits	Search Text	DBs	Time Stamp
1	BRS	L1	18636	substrate with plastic	USPAT	2000/05/23 16:50
2	BRS	L2	13797	sputtered	USPAT	2000/05/23 16:51
3	BRS	L3	44553	sputtering	USPAT	2000/05/23 16:51
4	BRS	L4	350	reactively with 2	USPAT	2000/05/23 16:51
5	BRS	L5	240	(REACTIVELY WITH 3)	USPAT	2000/05/23 16:51
6	BRS	L6	25	1 and 4	USPAT	2000/05/23 16:51
7	BRS	L7	25	(5 AND 1)	USPAT	2000/05/23 16:51
8	BRS	L9	42	6 or 7	USPAT	2000/05/23 17:11
9	BRS	L10	1542	antireflective	USPAT	2000/05/23 17:11
10	BRS	L11	3279	antireflection	USPAT	2000/05/23 17:13
11	BRS	L12	82	1 and 10	USPAT	2000/05/23 17:13
12	BRS	L13	211	(11 AND 1)	USPAT	2000/05/23 17:13
13	BRS	L14	255	12 or 13	USPAT	2000/05/23 17:13
14	BRS	L15	47	2 and 14	USPAT	2000/05/23 17:13
15	BRS	L16	139	(14 AND 3)	USPAT	2000/05/23 17:14
16	BRS	L17	140	15 or 16	USPAT	2000/05/23 17:14
17	BRS	L18	108905	dielectric	USPAT	2000/05/23 17:14
18	BRS	L20	78	17 and 18	USPAT	2000/05/23 17:14